

LK-AF-633

LK-AF 633 ANTIFOAM EMULSIONS is high performance silicone based antifoam emulsions containing non-ionic surfactants and functional additives.

Foam formation is generally unwanted as it increases viscosity and reduces the density of liquids, thereby making stirring and transport difficult. It can also decrease the performance of the product, give application faults and decreases output. These antifoams not only effectively kill foam in low concentrations but also do not show any adverse environmental impact (when used in ETP) due to their inert nature (chemically and biologically) and ability to decompose.

FEATURES

- Extremely high performance, thus effective at very low concentrations (10-100 ppm)
- Non-Reactive
- Easy to dilute using water
- Compatible with other systems
- Effective over wide temperature ranges
- Contains preservatives to prevent microbial growth

APPLICATIONS

- Effluent Treatment
- Detergency
- Paper Industry & fermentation industry.
- Latex Manufacturing
- Oil and Natural gas production
- Agrochemical
- Construction (Cement processing)

PRODUCT SELECTION GUIDE

LK AF 633 is Special-purpose antifoam emulsion and its viscosity and solid content can be adjusted according to demand. LK-AF 633 concentrate gives the best economic value, especially for industries where it is used in diluted concentration.

PRODUCT CHART ¹					
Product Name	Appearance	Viscosity (by Ford cup B4)	Solid Content (%) 150°C for 1 hour	pH	Defoaming & Antifoaming Activity
LK-AF-633	Milky Off-White Emulsion	30-40	30-33	6.0-8.0	Less than 15 sec

SUGGESTED APPLICATION METHOD AND FORMULATION

The best diluent for LK-AF-633 Antifoam emulsions is cold water. This emulsion is stable up to reasonable levels of water hardness (200 ppm). Although the emulsion should be stable above 200-ppm hardness, it is advised to treat the water with a dilute aqueous solution of Sodium Ethylenediaminetetraacetic acid (Na-EDTA) to ensure stability of the emulsion by formation of complexes.

Advised usage of this product is from 5 to 50 ppm solids content, however results may be achieved at much lower concentrations. The required amount may change according to the nature and concentration of the surfactant, temperature and the degree of foam control required. The user is advised to optimize his process by initially testing the antifoam at higher concentrations (50 ppm) and then reducing the concentration to the desired level of foam control.

To find the weight of emulsion required (in kilograms) to obtain a required ppm solid content in 1000 liter water divide the required ppm by (10 x %solids)

E.g. To get a 50 ppm solution of a 25% solids emulsion $50/(10 \times 25) = 0.2$ kilograms emulsion should be added for every 1000 liters water.

Suggested Use:

1. After estimation of the required quantity of antifoam required, pre-dilute the emulsion 2-10 times in cold water under low shear (to ensure efficient dispersion). Use this pre-diluted material immediately. USE DM water (free bacteria) for dilution. Agitate the product prior to use. For sufficiently high levels of agitation.
2. Inject the antifoam into the system, preferably up stream to the point of foam generation.

PACKING

50 Kgs can, 200-kg drums & 1000 Tote.

SHELF LIFE

Six months in the original container from the date of production.

STORAGE & HANDLING

It is recommended that normal safety precautions (hand gloves & safety goggles) be taken while handling the product. The material should be stored in original ELKAY containers in a cool place and protected from direct exposure to sunlight.

The information provided to the customers in this data sheet is intended as a guideline and is provided in good faith. The Information is believed to be accurate. Changes may occur from system to system as methods of use and conditions are beyond our control, hence **users are requested to evaluate the recommendations before actual application to get desired performance.**

ELKAY CHEMICALS PVT. LTD. (ELKAY) Main Plant Office (MIDC, Bhosari) exclusively can provide you with a specific written warranty for a particular use. In the absence of this, ELKAY gives the sole **warranty that the product (or products) supplied will meet its sales specifications** (not provided on this sheet). ELKAY disclaims any other expressed or implied warranty. For current or required specifications, please contact your ELKAY distributor, representative or office.

ELKAY does not warrant the recommendations given within for their fitness for use, performance, efficacy or safety. Users are responsible for certification of use of their product and for complying with local legislation. Suggestions of use shall not be taken as inducements to infringe any patents or grant any license under a valid patent and are provided for illustrative purposes only.

Internal References: DX40101